

Repairing Triflex Cryl Paste

Product information

Applications

Triflex Cryl Paste is used to level out any unevenness in the substrate and any fleece overlaps or depressions in Triflex systems as well as for the adhesive bonding of profiles.

Properties

2-component pigmented paste with a polymethyl methacrylate resin (PMMA) base. Triflex Cryl Paste offers the following features:

- Fast-curing
- Solvent-free

Pack size

Drum

5.00 kg	Triflex Cryl Paste
0.30 kg	Triflex Catalyst (3 x 0.10 kg)
5.30 kg	

15.00 kg	Triflex Cryl Paste
0.90 kg	Triflex Catalyst (9 x 0.10 kg)
15.90 kg	

Colours

7032 Pebble grey

Storage

Can be stored unopened and unmixed for approx. 6 months in a cool, dry place above freezing. Keep container away from direct sunlight when in storage and on the construction site.

Conditions for use

Triflex Cryl Paste can be used at substrate and ambient temperatures of a minimum of 0°C and a maximum of +35°C. In enclosed spaces, always ensure forced ventilation with a minimum 7-fold air exchange per hour.



Preparation of the substrate

The substrate must be sound, dry and free of loose or adhesion-reducing particles. Ensure that structural measures are taken to prevent moisture penetration from underneath. Substrate adhesion must be tested on a case-by-case basis.

During application, the surface temperature must be at least 3°C above dew point. Below that, a separating film of moisture can form on the surface to be worked on (DIN 4108-5, table 1). See dew point temperature table.

Priming

Triflex Cryl Primer 276 for concrete and cement screeds

Mixing instructions

After thoroughly mixing the base resin, the corresponding catalyst quantity is added to and mixed with a slow-running mixing machine until there are no more lumps. Stirring time at least 2 min. Transfer to another receptacle and mix again.

Mixing ratio

Temperature range of:	
0°C to +25°C	15.00 kg base resin + 0.90 kg catalyst
+25°C to +35°C	15.00 kg base resin + 0.60 kg catalyst

Material consumption

Approx. 1.40 kg/m² per mm thickness on a smooth even surface

Repairing Triflex Cryl Paste



Product information

Pot life

Approx. 10 min. at +20°C

Drying time

Rainproof after: approx. 30 min. at +20°C
Can be walked on/recoated after: approx. 1 hr. at +20°C

Notes on special hazards

See Safety Data Sheet, section 2

Safety tips

See Safety Data Sheet, sections 7 and 8

Measures in case of fire or accidents

See Safety Data Sheet, sections 4, 5 and 6

General notes

We guarantee the consistently high quality of our products. Non-Triflex products must not be used with Triflex systems.

The advice we give in relation to the application of our products is based on extensive development and many years of experience, and is correct to the best of our knowledge. Given the multitude of on-site requirements, under the most varied of conditions, the user is required to test the product's suitability for its respective purpose. Technical information is subject to change without notice in the interests of technical advancement or enhancement of our products.