



Product information

Applications

Triflex ProPark is used in the systems Triflex ProPark and Triflex AWS. It is a high-quality and durable fleece-reinforced surface waterproofing product for use in both new buildings and refurbishments.

Properties

2-component pigmented waterproofing with a polymethyl methacrylate resin (PMMA) base. Triflex ProPark is reinforced with Triflex Special Fleece and offers the following features:

- Highly flexible
- Rapidly resistant
- Seamless
- Easy to use
- Mechanically strong
- Vapour-permeable
- Elastic and crack-bridging
- Solvent-free

Pack size

Drum

| Summer | Winter | |
|----------|----------|---------------------------------------|
| 25.00 kg | 25.00 kg | Triflex ProPark base resin * |
| 0.50 kg | 1.00 kg | Triflex Catalyst (5 x / 10 x 0.10 kg) |
| 25.50 kg | 26.00 kg | |

Container

| Summer | Winter | |
|-----------|-----------|---------------------------------------|
| 500.00 kg | 500.00 kg | Triflex ProPark base resin * |
| 10.00 kg | 20.00 kg | Triflex Catalyst (1 x / 2 x 10.00 kg) |
| 510.00 kg | 520.00 kg | |

| Summer | Winter | |
|-------------|-------------|---------------------------------------|
| 999.00 kg | 999.00 kg | Triflex ProPark base resin * |
| 20.00 kg | 40.00 kg | Triflex Catalyst (2 x / 4 x 10.00 kg) |
| 1,019.00 kg | 1,039.00 kg | |

Disposable IBC

| Summer | Winter | |
|-------------|-------------|---------------------------------------|
| 1,250.00 kg | 1,250.00 kg | Triflex ProPark base resin * |
| 30.00 kg | 50.00 kg | Triflex Catalyst (3 x / 5 x 10.00 kg) |
| 1,280.00 kg | 1,300.00 kg | |

* Triflex ProPark base resin is produced according to the season in summer or winter formulations. See product label.

Colours

7030 Stone grey
7043 Traffic grey B



Storage

Can be stored unopened and unmixed for approx. 6 months in a cool, dry place above freezing. Keep container away from direct sunlight when in storage and on the construction site.

Conditions for use

Triflex ProPark can be applied at substrate and ambient temperatures between 0°C and +35°C. In enclosed spaces, always ensure forced ventilation with a minimum 7-fold air exchange per hour.

Preparation of the substrate

The substrate must be sound, dry and free of loose or adhesion-reducing particles. Ensure that structural measures are taken to prevent moisture penetration from underneath. Substrate adhesion must be tested on a case-by-case basis.

During application, the surface temperature must be at least 3°C above dew point. Below that, a separating film of moisture can form on the surface to be worked on (DIN 4108-5, table 1). See dew point temperature table.

Mixing instructions

After thoroughly mixing the base resin, the corresponding catalyst quantity is added to and mixed with a slow-running mixing machine until there are no more lumps. Stirring time at least 2 min.

Mixing ratio

| Temperature range of: | |
|-----------------------|--|
| 0°C to +5°C | 25.00 kg base resin + 1.00 kg catalyst |
| +5°C to +15°C | 25.00 kg base resin + 1.00 kg catalyst |
| +15°C to +35°C | 25.00 kg base resin + 0.50 kg catalyst |



Product information

Material consumption

Min. 3.00 kg/m² on a smooth, even surface

Pot life

Approx. 15 min at +20 °C

Drying time

| | |
|----------------------------------|---------------------------|
| Rainproof after: | approx. 1 hr. at +20 °C |
| Can be walked on/recoated after: | approx. 1 hr. at +20 °C |
| Resistant after: | approx. 3 hrs. at +20 °C |
| Resistant to chemicals after: | approx. 24 hrs. at +20 °C |

Notes on special hazards

See Safety Data Sheet, section 2

Safety tips

See Safety Data Sheet, sections 7 and 8

Measures in case of fire or accidents

See Safety Data Sheet, sections 4, 5 and 6

General notes

We guarantee the consistently high quality of our products. Non-Triflex products must not be used with Triflex systems.

The advice we give in relation to the application of our products is based on extensive development and many years of experience, and is correct to the best of our knowledge. Given the multitude of on-site requirements, under the most varied of conditions, the user is required to test the product's suitability for its respective purpose. Technical information is subject to change without notice in the interests of technical advancement or enhancement of our products.