#### Marking

# Triflex Cryl M 266

# X

## **Product information**

#### **Applications**

Triflex Cryl M 266 is used for the decorative, thick-layer marking of parking surfaces in the Triflex DMS system. Both lines and symbols can be marked.

#### **Properties**

2-component pigmented marking product with a polymethyl methacrylate resin (PMMA) base. Triflex Cryl M 266 offers the following features:

- Weatherproof
- Highly abrasion-resistant
- Solvent-free
- UV-resistant

#### Pack size

Drum

18.00 kg Triflex Cryl M 266 base resin 0.40 kg Triflex Catalyst (4 x 0.10 kg)

18.40 kg

#### **Colours**

1023 Traffic yellow 2009 Traffic orange 3020 Traffic red 4006 Traffic purple 5017 Traffic blue 6024 Traffic green 9010 White

#### Storage

Can be stored unopened and unmixed for approx. 6 months in a cool, dry place above freezing. Keep container away from direct sunlight when in storage and on the construction site.

#### **Conditions for use**

Triflex Cryl M 266 can be used at substrate and ambient temperatures of a minimum of  $0^{\circ}$ C and a maximum of  $+35^{\circ}$ C. In enclosed spaces, always ensure forced ventilation with a minimum 7-fold air exchange per hour.





#### Preparation of the substrate

The substrate must be sound, dry and free of loose or adhesion-reducing particles. Ensure that structural measures are taken to prevent moisture penetration from underneath. Substrate adhesion must be tested on a case-by-case basis.

During application, the surface temperature must be at least  $3 \,^{\circ}$ C above dew point. Below that, a separating film of moisture can form on the surface to be worked on (DIN 4108-5, table 1). See dew point temperature table.

#### Mixing instructions

After thoroughly mixing the base resin, the corresponding catalyst quantity is added to and mixed with a slow-running mixing machine until there are no more lumps. Stirring time at least 2 min.

#### **Mixing ratio**

Temperature range of:

 $0 \,^{\circ}\text{C}$  to +25  $\,^{\circ}\text{C}$  18.00 kg base resin + 0.40 kg catalyst +25  $\,^{\circ}\text{C}$  to +35  $\,^{\circ}\text{C}$  18.00 kg base resin + 0.20 kg catalyst

#### **Material consumption**

Min. 4.00 kg/m² on a smooth, even surface

#### Pot life

Approx. 15 min at +20 °C

### Marking

# Triflex Cryl M 266



## **Product information**

#### **Drying time**

Rainproof after: approx. 20 min. at +20 °C
Can be walked on after: approx. 40 min. at +20 °C
Suitable for vehicle traffic after: approx. 1 hr. at +20 °C

#### Notes on special hazards

See Safety Data Sheet, section 2

#### Safety tips

See Safety Data Sheet, sections 7 and 8

#### Measures in case of fire or accidents

See Safety Data Sheet, sections 4, 5 and 6  $\,$ 

#### **General notes**

We guarantee the consistently high quality of our products. Non-Triflex products must not be used with Triflex systems.

The advice we give in relation to the application of our products is based on extensive development and many years of experience, and is correct to the best of our knowledge. Given the multitude of on-site requirements, under the most varied of conditions, the user is required to test the product's suitability for its respective purpose. Technical information is subject to change without notice in the interests of technical advancement or enhancement of our products.