

Instructions for use

Proper sealing with Triflex SmartTec



Proper sealing with Triflex SmartTec

1K product:

Triflex SmartTec is a solvent-free, 1-component liquid applied waterproofing that does not require the addition of a catalyst.

Open container:

Open the container with the Triflex Container Opener. Be careful and ensure that the product remains free of impurities.

Stir the resin:

Stir Triflex SmartTec with a wooden stirrer for at least 2 minutes until a consistent mass is formed.

Important note:

After removing the material, the container should be sealed airtight.

1. Apply the layer:

Apply Triflex SmartTec over the entire surface using a paint roller. For larger areas, we recommend using a universal roller. Volume: at least 1.50 kg/m².



Lay fleece cuts:

Lay the prefabricated fleece cuts, removing any air bubbles. We recommend using Triflex Special Fleece PF as this soaks better.

Press the fleece down:

Press down the fleece you've just laid using a dry roller to get rid of any air pockets.

2. Apply the layer:

Apply Triflex SmartTec fresh-in-fresh over the entire surface until the fleece is no longer visible. Volume: at least 1.50 kg/m².

Important note:

For bonded sealing, use 2nd layer of Triflex SmartTec at least 2.00 kg/m² as well as fresh quartz sand sprinkling, grain size 0.7–1.2 mm in excess min. 7.00 kg/m².

Triflex SmartTec spray application:

Triflex SmartTec can also be applied by machine.

Triflex SmartTec including accessories:

Please follow the instructions in the product information.

International

Triflex GmbH & Co. KG
Karlstrasse 59
32423 Minden
Fon +49 571 38780-708
international@triflex.com
www.triflex.com

