Coating

Triflex ProDeck



Product information

Applications

Triflex ProDeck is used as a high-quality, durable coating for heavy-duty surfaces in the Triflex ProDeck parking deck system.

Properties

3-component pigmented coating (self-levelling mortar) with a polymethyl methacrylate resin (PMMA) base. Triflex ProDeck offers the following features:

- Self-levelling
- Fast-curing
- Weather-resistant
- Waterproof
- Wear-resistant
- Solvent-free
- UV-resistant
- Suitable for vehicle traffic
- · Withstands high mechanical loads

Winter

10.00 kg

Pack size

Drum/paper sack Summer

10.00 kg

23.00 kg 0.60 kg 33.60 kg	Triflex ProDeck S powder Triflex Catalyst (2 x / 6 x 0.10 kg)
Winter 500.00 kg	Triflex ProDeck R base resin *
1,150.00 kg	Triflex ProDeck S powder (50 x 23.00 kg)
30.00 kg	Triflex Catalyst (1 x / 3 x 10.00 kg)
	0.60 kg 33.60 kg Winter 500.00 kg 1,150.00 kg

Triflex ProDeck R base resin *

Summer	Winter	
910.00 kg	910.00 kg	Triflex ProDeck R base resin *
2,093.00 kg	2,093.00 kg	Triflex ProDeck S powder (91 x 23.00 kg)
20.00 kg	60.00 kg	Triflex Catalyst (2 x / 6 x 10.00 kg)
3 023 00 kg	3 063 00 kg	

^{*} Triflex ProDeck R base resin is produced according to the season in summer or winter formulations. See product label.



Colours

Mid-grey 2

Storage

Can be stored unopened and unmixed for approx. 6 months in a cool, dry place above freezing. Keep container away from direct sunlight when in storage and on the construction site.

Conditions for use

Triflex ProDeck can be applied at substrate and ambient temperatures between 0 °C and +35 °C. In enclosed spaces, always ensure forced ventilation with a minimum 7-fold air exchange per hour.

Preparation of the substrate

The substrate must be sound, dry and free of loose or adhesion-reducing particles. Ensure that structural measures are taken to prevent moisture penetration from underneath. Substrate adhesion must be tested on a case-by-case basis.

During application, the surface temperature must be at least $3 \,^{\circ}$ C above dew point. Below that, a separating film of moisture can form on the surface to be worked on (DIN 4108-5, Table 1). See dew point temperature table.

Mixing instructions

23 kg of Triflex ProDeck S powder is mixed into 10 kg Triflex ProDeck R base resin with the slow-running mixing machine until there are no more lumps. Triflex Catalyst is then also added into the slow-running mixing machine until there are no more lumps. Stirring time at least 2 min.

Triflex ProDeck

X

Product information

Mixing ratio

The mixing ratio (parts by weight) for base resin: powder should be 10:23. The quantity of catalyst added depends on the temperature range.

Temperature range of:

0 °C to +5 °C 10.00 kg base resin + 0.60 kg catalyst +5 °C to +15 °C 10.00 kg base resin + 0.40 kg catalyst +15 °C to +35 °C 10.00 kg base resin + 0.20 kg catalyst

Material consumption

Top decks as per OS 11a: Min. 5.00 kg/m² on a smooth, even surface

Interior decks, underground car parks and ramps as per OS 11b: Min. 4.50 kg/m² on a smooth, even surface

Pot life

Approx. 15 min at +20 °C

Drying time

Rainproof after: approx. 30 min. at +20 °C
Can be walked on/recoated after: approx. 1 hr. at +20 °C
Resistant after: approx. 2 hrs. at +20 °C

Notes on special hazards

See Safety Data Sheet, section 2

Safety tips

See Safety Data Sheet, sections 7 and 8

Measures in case of fire or accidents

See Safety Data Sheet, sections 4, 5 and 6

General notes

We guarantee the consistently high quality of our products. Non-Triflex products must not be used with Triflex systems.

The advice we give in relation to the application of our products is based on extensive development and many years of experience, and is correct to the best of our knowledge. Given the multitude of on-site requirements, under the most varied of conditions, the user is required to test the product's suitability for its respective purpose. Technical information is subject to change without notice in the interests of technical advancement or enhancement of our products.